Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-09-8-01** **Date: 04/10/2018**

Project Name : Construction of Marriage Community hall Chikkabettahalli Village in ward No.03 of Yelahanka Assembly Constitutency.

Agency : Sri.H.V Omkarappa, Class-1 PWD Contractor, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(project)/Ynk Zone/WO/119/2017-18

Date of Receipt : 01-08-18

Sample ID No : 2018-08-01-01 /02

Customer ID : PCC(M10)

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M10 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 04/10/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC(M10)	M10	06/09/2018	04/10/2018	149.26 X 151.66 X 151.92	22636	**8.658**	303.7	13.4	13.7
2	PCC(M10)	M10	06/09/2018	04/10/2018	149.00 X 150.45 X 149.31	22418	**8.788**	310.3	13.8	
3	PCC(M10)	M10	06/09/2018	04/10/2018	149.06 X 151.90 X 150.15	22642	**8.904**	314.6	13.9	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-07-24-01** **Date: 28/07/2018**

Project Name : Construction of Marriage Community hall Chikkabettahalli Village in ward No.03 of Yelahanka Assembly Constitutency.

Agency : Sri.H.V Omkarappa, Class-1 PWD Contractor, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(project)/Ynk Zone/WO/119/2017-18

Date of Receipt : 24-07-18

Sample ID No : 2018-07-24-01 /03

Customer ID : M20 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 29/07/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M20 Concrete	M20	22/07/2018	29/07/2018	151.42 X 150.35 X 150.28	22766	8.175	382.5	16.8	17.3
2	M20 Concrete	M20	22/07/2018	29/07/2018	151.44 X 150.39 X 150.25	22775	8.198	391.7	17.2	
3	M20 Concrete	M20	22/07/2018	29/07/2018	150.47 X 150.66 X 150.69	22670	8.135	405.8	17.9	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-07-24-01**

Date: 28/07/2018

Project Name : Construction of Marriage Community hall Chikkabettahalli Village in ward No.03 of Yelahanka Assembly Constitutency.

Agency : Sri.H.V Omkarappa, Class-1 PWD Contractor, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(project)/Ynk Zone/WO/119/2017-18

Date of Receipt : 24-07-18

Sample ID No : 2018-07-24-01 /05

Customer ID : M20 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 29/07/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M20 Concrete	M20	22/07/2018	29/07/2018	151.90 X 150.54 X 150.18	22867	8.443	393.3	17.2	17.4
2	M20 Concrete	M20	22/07/2018	29/07/2018	150.64 X 151.26 X 150.76	22786	8.055	403.3	17.7	
3	M20 Concrete	M20	22/07/2018	29/07/2018	149.15 X 150.98 X 149.19	22518	8.300	391.8	17.4	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

Page 1/1
****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-07-24-01** **Date: 28/07/2018**

Project Name : Construction of Marriage Community hall Chikkabettahalli Village in ward No.03 of Yelahanka Assembly Constitutency.

Agency : Sri.H.V Omkarappa, Class-1 PWD Contractor, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(project)/Ynk Zone/WO/119/2017-18

Date of Receipt : 24-07-18

Sample ID No : 2018-07-24-01 /07

Customer ID : M20 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 29/07/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M20 Concrete	M20	22/07/2018	29/07/2018	151.90 X 150.54 X 150.18	22867	8.443	409.3	17.9	17.7
2	M20 Concrete	M20	22/07/2018	29/07/2018	150.64 X 151.26 X 150.76	22786	8.055	403.3	17.7	
3	M20 Concrete	M20	22/07/2018	29/07/2018	149.15 X 150.98 X 149.19	22518	8.300	396.3	17.6	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-07-24-01** **Date: 28/07/2018**

Project Name : Construction of Marriage Community hall Chikkabettahalli Village in ward No.03 of Yelahanka Assembly Constitutency.

Agency : Sri.H.V Omkarappa, Class-1 PWD Contractor, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(project)/Ynk Zone/WO/119/2017-18

Date of Receipt : 24-07-18

Sample ID No : 2018-07-24-01 /01

Customer ID : M20 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 29/07/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M20 Concrete	M20	22/07/2018	29/07/2018	149.63 X 151.47 X 150.27	22664	8.186	392.1	17.3	17.4
2	M20 Concrete	M20	22/07/2018	29/07/2018	149.68 X 149.63 X 151.05	22397	8.201	396.4	17.7	
3	M20 Concrete	M20	22/07/2018	29/07/2018	150.85 X 149.66 X 150.07	22576	8.163	386.1	17.1	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-07-24-01** **Date: 19/08/2018**

Project Name : Construction of Marriage Community hall Chikkabettahalli Village in ward No.03 of Yelahanka Assembly Constitutency.

Agency : Sri.H.V Omkarappa, Class-1 PWD Contractor, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(project)/Ynk Zone/WO/119/2017-18

Date of Receipt : 24-07-18

Sample ID No : 2018-07-24-01 /02

Customer ID : M20 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 19/08/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M20 Concrete	M20	22/07/2018	19/08/2018	151.44 X 150.35 X 150.47	22769	8.175	516.9	22.7	22.6
2	M20 Concrete	M20	22/07/2018	19/08/2018	150.63 X 150.41 X 150.76	22656	8.163	496.2	21.9	
3	M20 Concrete	M20	22/07/2018	19/08/2018	149.63 X 151.43 X 151.05	22658	8.169	523.4	23.1	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro BANGALORE Sig..... Date.....

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-07-30-01** **Date: 04/08/2018**

Project Name : Construction of Marriage Community hall Chikkabettahalli Village in ward No.03 of Yelahanka Assembly Constitutency.

Agency : Sri.H.V Omkarappa, Class-1 PWD Contractor, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(project)/Ynk Zone/WO/119/2017-18

Date of Receipt : 30-07-18

Sample ID No : 2018-07-30-01 /01

Customer ID : M25 Footing Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 04/08/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M25 Footing Concrete	M25	28/07/2018	04/08/2018	149.62 X 150.30 X 149.66	22488	8.518	483.5	21.5	21.7
2	M25 Footing Concrete	M25	28/07/2018	04/08/2018	150.18 X 149.09 X 149.96	22391	8.355	494.8	22.1	
3	M25 Footing Concrete	M25	28/07/2018	04/08/2018	151.24 X 149.44 X 150.22	22601	8.545	483.7	21.4	

FOR CIVIL Pro.

CIVIL PRO BANGALORE Sig..... Date.....

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-07-31-01** **Date: 05/08/2018**

Project Name : Construction of Marriage Community hall Chikkabettahalli Village in ward No.03 of Yelahanka Assembly Constitutency.

Agency : Sri.H.V Omkarappa, Class-1 PWD Contractor, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(project)/Ynk Zone/WO/119/2017-18

Date of Receipt : 31-07-18

Sample ID No : 2018-07-31-01 /01

Customer ID : M25 Footing Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 05/08/2018

SL No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M25 Footing Concrete	M25	29/07/2018	05/08/2018	149.62 X 150.30 X 149.66	22488	8.518	483.5	21.5	21.7
2	M25 Footing Concrete	M25	29/07/2018	05/08/2018	150.18 X 149.09 X 149.96	22391	8.355	494.8	22.1	
3	M25 Footing Concrete	M25	29/07/2018	05/08/2018	151.24 X 149.44 X 150.22	22601	8.545	483.7	21.4	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-07-30-01** **Date: 25/08/2018**

Project Name : Construction of Marriage Community hall Chikkabettahalli Village in ward No.03 of Yelahanka Assembly Constitutency.

Agency : Sri.H.V Omkarappa, Class-1 PWD Contractor, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(project)/Ynk Zone/WO/119/2017-18

Date of Receipt : 30-07-18

Sample ID No : 2018-07-30-01 /02

Customer ID : M25 Footing Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 25/08/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M25 Footing Concrete	M25	28/07/2018	25/08/2018	151.89 X 150.89 X 151.45	22917	8.046	632.5	27.6	27.8
2	M25 Footing Concrete	M25	28/07/2018	25/08/2018	151.04 X 151.80 X 149.82	22928	8.306	653.5	28.5	
3	M25 Footing Concrete	M25	28/07/2018	25/08/2018	152.00 X 149.77 X 150.39	22765	8.366	623.7	27.4	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/0

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-07-31-01** **Date: 05/08/2018**

Project Name : Construction of Marriage Community hall Chikkabettahalli Village in ward No.03 of Yelahanka Assembly Constitutency.

Agency : Sri.H.V Omkarappa, Class-1 PWD Contractor, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(project)/Ynk Zone/WO/119/2017-18

Date of Receipt : 31-07-18

Sample ID No : 2018-07-31-01 /01

Customer ID : M25 Footing Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 05/08/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M25 Footing Concrete	M25	29/07/2018	05/08/2018	149.62 X 150.30 X 149.66	22488	8.518	483.5	21.5	21.7
2	M25 Footing Concrete	M25	29/07/2018	05/08/2018	150.18 X 149.09 X 149.96	22391	8.355	494.8	22.1	
3	M25 Footing Concrete	M25	29/07/2018	05/08/2018	151.24 X 149.44 X 150.22	22601	8.545	483.7	21.4	

FOR CIVIL Pr

R KARTHIK RECHA
Authorized Signato
Quality Manag

CIVIL Pro Sig..... Date..... BANGALORE

Page 1/1
****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-07-31-01** **Date: 26/08/2018**

Project Name : Construction of Marriage Community hall Chikkabettahalli Village in ward No.03 of Yelahanka Assembly Constitutency.

Agency : Sri.H.V Omkarappa, Class-1 PWD Contractor, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(project)/Ynk Zone/WO/119/2017-18

Date of Receipt : 31-07-18

Sample ID No : 2018-07-31-01 /02

Customer ID : M25 Footing Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 26/08/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M25 Footing Concrete	M25	29/07/2018	26/08/2018	151.89 X 150.89 X 151.45	22917	8.046	632.5	27.6	27.8
2	M25 Footing Concrete	M25	29/07/2018	26/08/2018	151.04 X 151.80 X 149.82	22928	8.306	653.5	28.5	
3	M25 Footing Concrete	M25	29/07/2018	26/08/2018	152.00 X 149.77 X 150.39	22765	8.366	623.7	27.4	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-08-01-01** **Date: 06/08/2018**

Project Name : Construction of Marriage Community hall Chikkabettahalli Village in ward No.03 of Yelahanka Assembly Constitutency.

Agency : Sri.H.V Omkarappa, Class-1 PWD Contractor, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(project)/Ynk Zone/WO/119/2017-18

Date of Receipt : 01-08-18

Sample ID No : 2018-08-01-01 /01

Customer ID : M25 Footing Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 06/08/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M25 Footing Concrete	M25	30/07/2018	06/08/2018	149.62 X 150.30 X 149.66	22488	8.518	483.5	21.5	21.7
2	M25 Footing Concrete	M25	30/07/2018	06/08/2018	150.18 X 149.09 X 149.96	22391	8.355	494.8	22.1	
3	M25 Footing Concrete	M25	30/07/2018	06/08/2018	151.24 X 149.44 X 150.22	22601	8.545	483.7	21.4	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro BANGALORE Sig..... Date.....

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-08-01-01** **Date: 27/08/2018**

Project Name : Construction of Marriage Community hall Chikkabettahalli Village in ward No.03 of Yelahanka Assembly Constitutency.

Agency : Sri.H.V Omkarappa, Class-1 PWD Contractor, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(project)/Ynk Zone/WO/119/2017-18

Date of Receipt : 01-08-18

Sample ID No : 2018-08-01-01 /02

Customer ID : M25 Footing Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 27/08/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M25 Footing Concrete	M25	30/07/2018	27/08/2018	151.89 X 150.89 X 151.45	22917	8.046	632.5	27.6	27.8
2	M25 Footing Concrete	M25	30/07/2018	27/08/2018	151.04 X 151.80 X 149.82	22928	8.306	653.5	28.5	
3	M25 Footing Concrete	M25	30/07/2018	27/08/2018	152.00 X 149.77 X 150.39	22765	8.366	623.7	27.4	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-08-27-01** **Date: 01/09/2018**

Project Name : Construction of Marriage Community hall Chikkabettahalli Village in ward No.03 of Yelahanka Assembly Constitutency.

Agency : Sri.H.V Omkarappa, Class-1 PWD Contractor, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(project)/Ynk Zone/WO/119/2017-18

Date of Receipt : 27-08-18

Sample ID No : 2018-08-27-01 /01

Customer ID : M25 Plinth Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 01/09/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M25 Plinth Concrete	M25	25/08/2018	01/09/2018	150.30 X 151.27 X 151.84	22737	8.379	452.5	19.9	20.5
2	M25 Plinth Concrete	M25	25/08/2018	01/09/2018	151.33 X 150.22 X 151.32	22731	8.339	481.9	21.2	
3	M25 Plinth Concrete	M25	25/08/2018	01/09/2018	151.68 X 150.61 X 150.13	22844	7.981	468.3	20.5	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-08-27-01** **Date: 22/09/2018**

Project Name : Construction of Marriage Community hall Chikkabettahalli Village in ward No.03 of Yelahanka Assembly Constitutency.

Agency : Sri.H.V Omkarappa, Class-1 PWD Contractor, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(project)/Ynk Zone/WO/119/2017-18

Date of Receipt : 27-08-18

Sample ID No : 2018-08-27-01 /02

Customer ID : M25 Plinth Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 22/09/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M25 Plinth Concrete	M25	25/08/2018	22/09/2018	149.28 X 150.25 X 151.01	22430	8.144	639.3	28.5	28.9
2	M25 Plinth Concrete	M25	25/08/2018	22/09/2018	149.63 X 151.17 X 151.24	22620	8.145	671.8	29.7	
3	M25 Plinth Concrete	M25	25/08/2018	22/09/2018	151.93 X 151.90 X 149.19	23079	8.141	655.4	28.4	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 05/09/2018

Lab ID : **CP-2018-08-31-01**

Project Name : Construction of Marriage Community hall Chikkabettahalli Village in ward No.03 of Yelahanka Assembly Constitutency.

Agency : Sri.H.V Omkarappa, Class-1 PWD Contractor, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(project)/Ynk Zone/WO/119/2017-18

Date of Receipt : 31-08-18

Sample ID No : 2018-08-31-01 /01

Customer ID : M25 Column Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 05/09/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M25 Column Concrete	M25	29/08/2018	05/09/2018	150.42 X 150.54 X 150.45	22644	8.312	482.3	21.3	20.9
2	M25 Column Concrete	M25	29/08/2018	05/09/2018	150.42 X 150.54 X 150.45	22644	8.331	464.2	20.5	
3	M25 Column Concrete	M25	29/08/2018	05/09/2018	150.32 X 150.54 X 150.35	22629	8.345	470.7	20.8	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-08-31-01** **Date: 26/09/2018**

Project Name : Construction of Marriage Community hall Chikkabettahalli Village in ward No.03 of Yelahanka Assembly Constitutency.

Agency : Sri.H.V Omkarappa, Class-1 PWD Contractor, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(project)/Ynk Zone/WO/119/2017-18

Date of Receipt : 31-08-18

Sample ID No : 2018-08-31-01 /02

Customer ID : M25 Column Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 26/09/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M25 Column Concrete	M25	29/08/2018	26/09/2018	149.89 X 151.82 X 151.09	22757	8.195	648.6	28.5	28.2
2	M25 Column Concrete	M25	29/08/2018	26/09/2018	151.38 X 150.97 X 150.01	22853	8.238	635.3	27.8	
3	M25 Column Concrete	M25	29/08/2018	26/09/2018	151.24 X 151.72 X 151.90	22947	8.060	651.7	28.4	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

Page 1/1
****End of Report****